

## KEMFLOR 522 SL

### WATER BASED EPOXY – SELF LEVELING

Rev.00-241110

#### PRODUCT DESCRIPTION

Kemflor 522 SL is a Water Based epoxy floor coating for use in industrial and commercial environments. It produces a smooth, self-leveling Matt finish with several advantages:

- Good chemical resistance
- Good abrasion resistance
- Free of solvents
- High mechanical strength
- Provides a hygienic surface (easy to clean)
- Easy & fast application
- Floor can be put in use quickly
- Durability
- Seamless
- Aesthetic: Available in several colors

#### INTENDED USES

Kemflor 522 SL can be used where a durable and easy to clean floor surface is required. Some typical applications include:

- Pharmaceutical industry
- Chemical industry
- Food processing industry
- Electronic Assembly
- Dairies / breweries
- Clean rooms
- Hospitals
- Laboratories
- Packaging industry
- Workshops
- Factory shop floors
- Kitchens

#### SPECIFICATION DATA

<b>Thickness</b>	1 mm	2 mm
<b>Type</b>	3 pack	3 pack
<b>Shade</b>	Limited	Limited
<b>Finish</b>	Matt	Matt
<b>Chemical Base</b>	WB Epoxy Polyamide	WB Epoxy Polyamide
<b>Mixing Ratio</b>	3:1:6/wt	3:1:6/wt
<b>Coverage kg/sq.m.</b>	3	5.8
<b>Recommended No. Of Coats</b>	1	1
<b>Re-coating Interval</b>	Min. 16 hrs	Min. 16 hrs
<b>Surface Dry Time</b>	6 hrs	6 hrs
<b>Curing Time</b>	7 days	7 days
<b>Pot Life</b>	30 min.	30 min.
<b>Shelf Life (under std. condition)</b>	12 months	12 months
<b>Recommended System</b>	Various	Various
<b>Pack Size</b>	30 kg	-



#### Chembond Chemicals Limited

Chembond Centre  
EL-71, MIDC Mahape,  
Navi Mumbai 400 710  
INDIA

Tel: (91 22) 66143000 / 315  
Fax: (91 22) 768 1294  
E-mail: sales@chembondcoatings.com  
Website: www.chembondindia.com

## KEMFLOR 522 SL

### WATER BASED EPOXY – SELF LEVELING

Rev.00-241110

**Note:** These figures are theoretical under controlled conditions and may vary depending upon site conditions i.e. temp., humidity, surface porosity, surface profile, handling of material etc.

#### DIRECTION OF USE

##### **SURFACE PREPARATION:**

As is the case with every coating scheme, the surface profile is of utmost importance. In order to achieve optimum bonding between substrate and coating, it is necessary to apply product only on fully dry and neatly cleaned surfaces.

**New concrete floors: KemFlor 522 can be applied on Green concrete.**

##### **Precautionary measures for old concrete floors:**

Surface should be free from dust, grease, oil, laitance, loose material, old coatings etc. Generally cleaning with Kleenol or equivalent is enough to remove grease/oil. Smooth, aged concrete may be etched with dilute hydrochloric acid for suitable roughness and better adhesion of the epoxy flooring. In case of heavy oil & grease contamination, existing partial coating or structurally unsound concrete layer has occurred or old coatings are present mechanical cleaning is advisable.

##### **KEMFLOR 522 APPLICATION:**

After surface preparation depending upon the system adopted KemFlor 522 SL can be applied on primer. Mix Kemflor 522 SL in the ratios given below by weight. It is advisable to use entire contents of each can to ensure accurate proportions and to enable estimation of consumption.

Add the parts in the sequence below, under continuous stirring by a very slow speed electric stirrer or jitty blade mixer fitted on an electric drill till the mixture is homogeneous. **DO NOT MIX BY HAND.** Remove all material from each can. Scrape the sides of the container several times to ensure complete mixing. Be careful to not introduce any air bubbles while mixing. Since the mix ratio is critical to the performance of the flooring system, it is advisable to mix the entire contents of the three parts as supplied.

Pour the mixed Kemflor 522 SL onto the surface as soon as possible (See pot life) and spread using a serrated trowel. Immediately after the trowel application, a spiked roller should be used to ensure a level homogenous surface free of voids and surface imperfections.

Do not overwork the material. Apply slowly to minimize bubbling. If bubbles appear, use a porcupine roller to produce a bubble free film. Kemflor 522 SL is designed for use without solvents, use of thinners is not recommended.

#### CLEAN UP

For cleaning of application equipment and tools use water.



#### **Chembond Chemicals Limited**

Chembond Centre  
EL-71, MIDC Mahape,  
Navi Mumbai 400 710  
INDIA

Tel: (91 22) 66143000 / 315  
Fax: (91 22) 768 1294  
E-mail: sales@chembondcoatings.com  
Website: www.chembondindia.com

## KEMFLOR 522 SL

### WATER BASED EPOXY – SELF LEVELING

Rev.00-241110

MAINTENANCE	SAFETY PRECATIONS
<p>For maximum life expectancy, routinely sweep and wash floors with conventional detergent cleaners. Do not steam clean: all spills powder or liquid should be cleaned up immediately. Inspect the floor regularly for wear, breaks or damages, if found any immediately consult with Chembond's technical service personnel or authorized applicator.</p>	<p>Take care to avoid skin or eye contact and breathing vapours. In the event of the skin contact immediately wash thoroughly. In the event of eye contact, wash continuously for 15 minutes in water and seek medical advice. Wear protective clothing, gloves, and safety glasses while using this product. If inhalation occurs, move to fresh air and seek medical advice in case of difficulty in breathing. Keep material away from heat, flames, and sources of ignition. For further details read Material Safety Data Sheet.</p>
LIMITATIONS OF LIABILITY	
<p>This information is based on our current level of knowledge. It is given in a good faith but it is not intended to guarantee any particular properties. The users must satisfy themselves that there are no circumstances requiring additional information or precautions or the verification of details given herein.</p>	



#### Chembond Chemicals Limited

Chembond Centre  
 EL-71, MIDC Mahape,  
 Navi Mumbai 400 710  
 INDIA

Tel: (91 22) 66143000 / 315  
 Fax: (91 22) 768 1294  
 E-mail: sales@chembondcoatings.com  
 Website: www.chembondindia.com